

EternaCaulk

Description

EternaCaulk is a high-performance, multipurpose thermoplastic elastomer based sealant. It can be applied to dry or wet surfaces. **EternaCaulk** provides excellent adhesion to most roof surfaces including metal, Kynar coated metal, asphalt, shingles, modified bitumen, EPDM, TPO, Elvaloy/PVC, Hypalon, vinyl, fiber cement, wood, concrete, tile, masonry, and glass. **EternaCaulk** meets all federal standards for health and environmental safety. **EternaCaulk** is available in clear, white and black.

Basic Use

EternaCaulk is used to seal roof joints (seams) and tears, flashings, copings, skylights, gutters, etc. It can be used to fill holes on most roofing materials. **EternaCaulk** is compatible with all **EternaBond MicroSealant™** tapes and is ideal for roofing applications where appearance is important.

Composition

EternaCaulk is a thermoplastic elastomer based sealant with a roofing approved VOC <250 g/l (compliant in 50 states).

Surface Preparation

Surface to be sealed must be clean and dry. Remove heavy accumulations of loose rust and scale, dust, talc and dirt. Oil, grease and other contaminants should be removed with **EternaClean** or a non-residue cleaner. Porous surfaces may be primed with **EternaPrime** prior to application of this product.

*Do not use **EternaPrime** on PVC roofs as reactivation of some plasticizers may occur.

Technical Data

Adhesion ASTM C-794 to:

Aluminum	26 lbs. per linear inch
Cement/Mortar	22 lbs. per linear inch
Asphalt	20 lbs. per linear inch
EPDM	15 lbs. per linear inch
PVC/KEE	15 lbs. per linear inch
Shingle	19 lbs. per linear inch
Steel	15 lbs. per linear inch
TPO	11 lbs. per linear inch
Wood	22 lbs. per linear inch
Available colors	Clear, White, Black
Container sizes	10 oz. tubes
Elongation ASTM D-412	1000% @ 77° F (25° C)
Flash point (TCC)	+51° F (38.7° C)
% Non-Volatile	75 max.
% Solids by volume	68 min.
Tensile strength	800 psi min.
VOC	<250 g/l (compliant in 50 states)

Values are typical performance properties and characteristics based on laboratory testing. This is intended as a guide for comparison purposes and does not constitute a specification or specification range.

Application

To use, cut top to size and puncture seal. Maximum recommended joint width and depth is 3/8 inch. Use backer rod for deep joints.

CAUTION: All statements and technical information in this document are based on tests or data that ADCO believes is reliable. However, ADCO does not warrant or guarantee the accuracy or completeness of this information. The user has sole knowledge and control of factors that can affect the performance of ADCO's products in the user's intended application. It is the user's responsibility to conduct tests to determine the compatibility of ADCO's product with the design, structure, and materials of the user's end product and the suitability of ADCO's product for the user's method of application and intended use. The user assumes all risk and liability arising out of such use.

Available from Major Electronix | sales@majorelectronix.com | 800-966-2345 | www.productsforautomation.com

EternaBond EternaCaulk 08/11/11

WARRANTY: ADCO warrants its products to conform to ADCO's specifications at the time of sale when tested according to ADCO standards. If a product is proven to be defective when tested according to ADCO standards, ADCO will, at its option, refund the purchase price or replace or repair the defective product. THIS LIMITED WARRANTY IS THE BUYERS SOLE AND EXCLUSIVE REMEDY AGAINST ADCO AND IS IN LIEU OF ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. In no event shall ADCO be liable for any special, incidental, consequential, or punitive damages arising out of any claims whether based on negligence, contract, warranty, strict liability or otherwise.

